



MATERIAL


High Tear Resistant and High Elongation Vacuum Grade Silicone

AVAILABLE GRADES

Standard 1.8m wide in 50° shore A, for wider widths refer to our BlueVac grades

TEMPERATURE

Temperature Range



GENERAL INFORMATION

Premium quality high tear and high elongation silicone membrane sheets for vacuum forming applications. SuperVac sheetings have an extreme high tear resistance as well as high elongation, excellent abrasion resistance, longevity and are repairable.

ENVIRONMENTAL RESISTANCE

Silicone rubber products have an excellent resistance to:

- ❖ Ozone
- ❖ Oxidation
- ❖ Ultraviolet light
- ❖ Corona discharge
- ❖ Cosmic radiation
- ❖ Ionising radiation
- ❖ Weathering in general

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

MVQ SILICONES GMBH

Industriepark Hertzstrasse, Hertzstrasse 11, D-69469 Weinheim, Deutschland, Tel 0049 6201 259040, Fax 0049 6201 2590410

E-Mail: info@mvq-silicones.de, Website: www.mvq-silicones.de, Registered in Germany No. HRB 701069

Director: K Soudah



AVAILABILITY FORMAT

- ✓ Supplied in continuous roll lengths up to 10m long
- ✓ Widths of 1800mm (standard)
- ✓ 1.0mm, 1.5mm, 2.0mm, 3.0mm (standard thickness)
- ✓ Translucent with a blue tint

TYPICAL APPLICATIONS

- ❖ Automotive carbon fibre lamination
- ❖ Solar panel lamination
- ❖ Veneer lamination
- ❖ Wood panel lamination

MECHANICAL PROPERTIES

PROPERTY	UNITS	SPEC LIMITS	TYPICAL VALUE	TEST METHOD
HARDNESS	Shore A	± 5	50	ASTM D2240 DIN 53505
TENSILE STRENGTH	MPa (PSI)	7.0 min (1015 min)	8.5 (1233)	BSISO 37 ASTM D412 die C
ELONGATION TO FAILURE	%	600 min	750	BSISO 37 ASTM D412 die C
TEAR STRENGTH	N/mm (lb./in.)	35.0 min 200 min	40.0 228	ASTM D624 die B
COMPRESSION SET 25% COMPRESSION 24 HRS AT 150°C 30MIN RECOVERY	%	-	24	BS 903 pt A6 type B DIN/ISO 815 type B

In-house capabilities for extensive industry specific testing available on request

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

MVQ SILICONES GMBH

Industriepark Hertzstrasse, Hertzstrasse 11, D-69469 Weinheim, Deutschland, Tel 0049 6201 259040, Fax 0049 6201 2590410

E-Mail: info@mvq-silicones.de, Website: www.mvq-silicones.de, Registered in Germany No. HRB 701069

Director: K Soudah



GENERAL CHARACTERISTICS

TEST	RESULT	STANDARD
BRITTLE POINT	-80°C (-112 °F)	ASTM D746
LIMITING OXYGEN INDEX	24.0 %	BS 2782 Part 1
THERMAL CONDUCTIVITY	0.24 W.m ⁻¹ .K ⁻¹	VDE 0304
RADIATION RESISTANCE	>10 ⁵ Grays (10 ⁷ Rads) typical	
DIELECTRIC STRENGTH	23 kV.mm ⁻¹	VDE 0303
DIELECTRIC CONSTANT	2.9	VDE 0303
DISSIPATION FACTOR	3x10 ⁻⁴	VDE 0303
VOLUME RESISTIVITY	3x10 ¹⁵ Ω.cm	VDE 0303

ACCREDITATIONS

- ❖ REACH compliant
- ❖ RoHS compliant

ADDITIONAL INFORMATION

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

MVQ SILICONES GMBH

Industriepark Hertzstrasse, Hertzstrasse 11, D-69469 Weinheim, Deutschland, Tel 0049 6201 259040, Fax 0049 6201 2590410

E-Mail: info@mvq-silicones.de, Website: www.mvq-silicones.de, Registered in Germany No. HRB 701069

Director: K Soudah